



ABCESAR
MINERALS AND COLOURS

Grès de Thiviers

OJ 3

**TYPICAL PROPERTIES / PROPRIETES
TYPIQUES**

CHEMICAL ANALYSIS / ANALYSE CHIMIQUE	(%)
SiO ₂	50,00 -60,00
Fe ₂ O ₃	4,00 – 10,00
TiO ₂	30,00 – 40,00
Al ₂ O ₃	<1
Na ₂ O	<1
K ₂ O	<0,5
MgO	<0,5

PARTICLE SIZE / GRANULOMETRIE

45 µm

FIRED PROPERTIES / PROPRIETES A LA CUISSON

Melting point / Point de fusion > 1500

COLOUR CHARACTERISTICS / CARACTERISTIQUES COULEUR

Before firing / Avant cuisson yellow ochre / ocre jaune

After firing / Après cuisson yellow orange / ocre orange

BULK DENSITY / DENSITE (g/cm³)

1,40

PACKAGING / CONDITIONNEMENT

Powder form in / Poudre en Big Bags

25Kg Bags

Production Site / Site de Production

ABCesar
La Terre des Landes
24340 Saint-Sulpice de Mareuil
FRANCE

Tél. : + 33 (0)5 53 60 86 60
Fax : + 33 (0)5 53 60 86 62
eMail: contact@abcesar.com

The data quoted are determined by use of standard test methods, copies of which will be supplied on request. Every precaution is taken in production to ensure the products conform to our published data. Since the products are based on naturally occurring materials, we reserve the right to change these data should it become necessary. Sales are in accordance with our "Conditions of Sale", copies of which will be supplied on request.

Les renseignements techniques contenus dans cette fiche sont donnés en toute bonne foi et à titre indicatif ; ils ne peuvent faire l'objet d'une garantie. Nous nous réservons le droit de modifier ces informations si nécessaire. Les caractéristiques, exprimées avec des tolérances, correspondent aux paramètres contrôlés, conformément au cahier des charges qualité interne. Les autres caractéristiques sont issues du traitement statistique moyen annuel. Les conditions de vente de nos produits sont disponibles auprès de notre réseau commercial.