



TERRA RARA CeO_x – Rare Earth CeO_x:

CERIOX 99,5

Consigliato nella fusione di fritte ceramiche per ottenere l'effetto lustro.
Suggested in melting ceramic frits to get luster effect .

Analisi Chimica / Chemical analysis

CeO ₂	99,50 %
La ₂ O ₃	0,12 %
Pr ₆ O ₁₁	0,04 %
Nd ₂ O ₃	0,009 %
Sm ₂ O ₃	0,005 %
Y ₂ O ₃	0,005 %
Fe ₂ O ₃	0,010 %
SiO ₂	0,010 %
ZnO	0,010 %
CaO	0,001 %
LOI	< 0,5 %

(XRF data)

Imballaggio / Packaging : S25kg/bb1000kg su paletta – 25kbags/bb1000kg on pallet

Analisi Granulometrica / Particle Size

200 mesh



BAAN Industrial Raw Materials

Via Maestri del Lavoro n°10 – 41043 Colombaro di Formigine - Italia

Cell: +39.335.7740438 – Tel/Fax: +39.059.553.283

email: baanrawmaterials@alice.it ; sito web: info@baanmaterials.com