



DOLOMITE: DOLOMITE 100

Indicato per formulazioni di impasto da monoporosa e da bicottura bianca da rivestimento.
Suggested for monoporosa and white double fast firing spongy dried bodies for wall tiles.

Analisi Chimica / Chemical Analysis

SiO ₂	0,080 %
Al ₂ O ₃	0,018 %
Fe ₂ O ₃	0,022 %
CaO	30,660 %
MgO	21,600 %
L.O.I.	47,62 %
Density	2,88 gr/cm ³

Granulometria / Particle size

- 1 – 200 micron
-200 – 700 micron
- 0,7 – 1,3 mm
-1,0 – 3,0 mm

Analisi Mineralogica / Mineralogical Analysis

Dolomite 100,00 %



BAAN Industrial Raw Materials
Via Maestri del Lavoro n°10 – 41043 Colombaro di Formigine
Cell: +39.335.7740438 – Tel/Fax: +39.059.553.283
email: baanrawmaterials@alice.it ; web site: www.baanmaterials.com