



**TERRA RARA Er<sub>2</sub>O<sub>3</sub> – Rare Earth Er<sub>2</sub>O<sub>3</sub>:**

**ERBIOX 99,5**

Consigliato nella fusione di fritte ceramiche e nei vetri per ottenere effetti estetici.  
Suggested in melting ceramic frits and glasses to get aesthetical effects .

**Analisi Chimica / Chemical analysis**

---

Er <sub>2</sub> O <sub>3</sub>	99,500 %
Y <sub>2</sub> O <sub>3</sub>	0,100 %
T <sub>2</sub> O <sub>3</sub>	0,100 %
Yb <sub>2</sub> O <sub>3</sub>	0,100 %
Fe <sub>2</sub> O <sub>3</sub>	0,010 %
SiO <sub>2</sub>	0,010 %
LOI	< 0,200 %

(XRF data)

Imballaggio / Packaging : S25kg/bb1000kg su paletta – 25kbags/bb1000kg on pallet

**Analisi Granulometrica / Particle Size**

---

200 mesh



**BAAN Industrial Raw Materials**  
Via Maestri del Lavoro n°10 – 41043 Colombaro di Formigine - Italia  
Cell: +39.335.7740438 – Tel/Fax: +39.059.553.283  
email: [baanrawmaterials@alice.it](mailto:baanrawmaterials@alice.it) ; sito web: [info@baanmaterials.com](http://info@baanmaterials.com)