



Feldspato Potassico – Potassic Feldspar:

S 15

Indicato per smalti ed impasti da gres porcellanato

Suggested for glazes and spray dried gres porcellanato bodies

Analisi Chimica – Chemical Analysis

SiO ₂	70,40 % +-0,80
Al ₂ O ₃	13,55 % +-0,40
Fe ₂ O ₃	0,38 % +-0,06
TiO ₂	0,14 % +-0,04
CaO	4,05 % +-0,30
MgO	0,84 % +-0,20
K ₂ O	9,08 % +-0,30
Na ₂ O	0,39 % +-0,10
L.O.I.	1,17 % +-0,20

Umidità – Moisture : 8% - 10%

Imballaggio – Packaging : sfuso su ribaltabile - bulk

Granulometrie – Particle Size : in granella - sand

Analisi Mineralogica – Mineralogical Analysis



BAAN Industrial Raw Materials

Via Maestri del Lavoro n°10 – 41043 Colombaro di Formigine

Cell: +39.335.7740438 – Tel/Fax: +39.059.553.283

email: baanrawmaterials@alice.it ; web site: www.baanmaterials.com