



PEGMATITE POTASSICA / POTASSIC PEGMATITE:

G 6

Indicata all'interno di smalti e per impasti da gres porcellanato

Suggested for glazes and spray dried gres porcellanato bodies

Analisi Chimica / Chemical Analysis

SiO ₂	85,60 %
Al ₂ O ₃	9,40 %
Fe ₂ O ₃	0,10 %
CaO	0,01 %
MgO	0,01 %
K ₂ O	3,95 %
Na ₂ O	0,15 %
L.O.I.	1,25 %

Imballaggio / Packaging: 25kg bags / bb1000kg on pallet

Analisi Mineralogica / Mineralogical Analysis

Anortite	0,00 %
Albite	1,60 %
Ortoclasio	24,60 %
Caolinite	8,50 %
Quarzo	64,90 %



BAAN Industrial Raw Materials

Via Maestri del Lavoro n°10 – 41043 Colombaro di Formigine - Italia

Cell: +39.335.7740438 – Tel/Fax: +39.059.553.283

email: info@baanmaterials.com ; web site: www.baanmaterials.com