



VETROCERAMICO FONDENTE :

GL 100

Graniglia vetrosa depurata e macinata

Fondente ricco in alcali ed alcalino terrosi, ottimo x impasti ceramici

Low melting glass , rich in Na-K and Sr-Ba , excellent for spray dried body formulations

Very cheap and suggested to replace standard Na-feldspar

Analisi Chimica / Chemical Analysis

SiO ₂	59,92 %
Al ₂ O ₃	2,00 %
Fe ₂ O ₃	0,06 %
TiO ₂	0,40 %
BaO	10,00 %
CaO	0,10 %
MgO	0,07 %
ZnO	0,70 %
K ₂ O	8,00 %
Na ₂ O	7,00 %
Li ₂ O	0,40 %
SrO	9,00 %
Sb ₂ O ₃	0,30 %
ZrO ₂	2,00 %
L.O.I.	0,05 %

Imballaggio / packaging: sfuso e BB1000kg su paletta ; bulk and bb1000kg on pallet

Granulometria / particle size

In granuli , da 1 a 20 mm

In pezzi , da 3cm a 10cm



BAAN Industrial Raw Materials

Via Maestri del Lavoro n°10 – 41043 Colombaro di Formigine - Italia

Cell: +39.335.7740438 – Tel/Fax: +39.059.553.283

email: info@baanmaterials.com ; web site: www.baanmaterials.com