



**WOLLASTONITE : W200CG**

Wollastonite micronizzata ad alta purezza , suggerita per fritte, smalti e per impasti da porcellanato  
High purity micronized wollastonite, suggested for frits, glazes, and for gres porcellanato spray dried body

**Analisi Chimica / Chemical Analysis**

---

SiO <sub>2</sub>	min 49,00 %
CaO	min 45,00 %
Fe <sub>2</sub> O <sub>3</sub>	0,25 %
MgO	0,95 %
LOI	2,50 %

Colore / color : bianco / white

Granulometria / particle size: micronized < 75microns

Imballaggio / packaging: bb 1000kg – S25kg

Wollastonite > 90%

**Analisi Granulometrica / Particle Size**

---

0,5% > 150micron

5,0% > 75micron

95,0% < 75micron



**BAAN Industrial Raw Materials**

Via Maestri del Lavoro n°10 – Formigine - Italia

Cell: +39.335.7740438 – Tel/Fax: +39.059.553.283

email: [baanrawmaterials@alice.it](mailto:baanrawmaterials@alice.it) ; web site: [www.baanmaterials.com](http://www.baanmaterials.com)